


CUSTOMER :	DATE:
ASRY – BAHRAIN for USS SQUALL	05/05/18
AREA DESCRIPTION:	INSTALLERS AND REPORT BY:
PC 7 – USS SQUALL – Forecastle portside	Sohail Ghori + ASRY team
CUSTOMER CONTACT:	REPORT CIRCULATION:
Amr Shaker	SFET / SNSS









Silvagrip[®] INSTALLATION REPORT:

TOTAL AREA OF COVERAGE

Main deck frame 0-55 USS SQUALL – Laser cut panels

INSTALLATION TIME

8 HOURS, Forecastle portside

WEATHER CONDITIONS

Very Hot – 42 degree C Humidity approximately 70%

<u>METHOD</u>

Safely loaded materials and tools aboard USS SQUALL informing NAVY Surveyor. USS SQUALL Deck is coated PPG Amercoat 137 base and PPG PSX 700SG top semi-gloss coating.

STEP 1 - Inspect and note condition of the area to be covered

USS SQUALL Deck is coated PPG Amercoat 137 base and PPG PSX 700SG top semi-gloss coating.

STEP 2 – Clean-down 1

Cleaned the surface with Industrial Cleaning Cloths.

STEP 3 – Plan the Installation

Laid out the Silvagrip panels onto the surface as per each panel number referring to the drawing to inspect each panel and to visualise the area to be covered before fixing.

STEP 4 – Clean-down 2

After establishing the area each panel area was cleaned with acetone. The acetone acts as a deep degrease agent and will also etch the surface slightly allowing a strong key effect of the adhesive and edge sealer

STEP 5 – Apply the Silvagrip to the Cleaned area

Removed the backing film of the Silvagrip by piercing the film in the corner of the panel with the small blade of a penknife and peeling back the blade. Once the corner of the backing film is free the peeling becomes quite easy although there is some resistance created by the adhesive. Discarded the film and immediately placed the Silvagrip panel into the correct in line position. Fixed the panel by applying finger pressure to the panel and expelling any air from the interface of the adhesive to the deck.

Silvagrip'





STEP 6 – Roll to adhere strongly

Used the rubber roller and 45 KG Roberts roller to apply pressure to the panel and create strong bond between the adhesive and the deck. Paid particular attention to the corners and edges of the panel.

STEP 7 – Apply Edge Sealer

Re-cleaned the edges of the panel with acetone and clean cloth. Applied the edge sealer via a cartridge gun applicator. The bead was around 3/16in and covered the top of the panel / coating slightly and the edge to deck surface.

REPEATED STEPS 4 – 7 TO COMPLETION

Visually inspected the installed panel on forecastle area after the completion to check if there are any gaps left while sealing.

AFTER CARE RECOMMENDATIONS

CLEANING

If heavy dirt build up occurs on the anti-slip surface this can be removed by using a pressure washer on a <u>low-pressure</u> setting.

If a pressure washer is not available a stiff bristle brush can be used with some detergent to loosen any embedded deposits. The surface can then be washed down with a hosepipe

Note. Care must be taken not to damage the Edge Seal when cleaning !!







The Non-Skid installation squad and USS SQUALL in the background





Silvagrip'



Surface Finishing Eigenment Trading LLC



Packed Silvagrip Material for USS SQUALL



Unpacking and checking the tools







Surface Finishing Eigelpment Trading LLC



Reviewing the drawing ASRY USS SQUALL project manager.



USS SQUALL - Forecastle Silvagrip panel layout drawing with markings







Surface Finishing Eigupment Trading LLC



Unpacking the silvagrip panels and tools



Laid the panels are per their each unique number specified on the drawing



Silvagrip'



Surface Finishing Explorement Trading LLC



- a) Protecting the paint on the deck by covering the shoes by polythene. Unique idea!
- b) Aligning the silvagrip panel and marking the area.
- c) Marking the gaps between the two panels.







Surface Finishing Equipment Trading LLC



Cleaning the area with Acetone.



Removing the back film with a pen knife.



Silvagrip'



Surface Finishing Explorement Trading LLC



Laying the Silvadrip down carefully.



Rolling the Silvagrip panel with a heavy roller. A hand roller can also be used.



Silvagrip'



Surface Finishing Eigepment Trading LLC



Sealing the edges of Silvagrip with Silva seal.






Silvagrip'



Surface Finishing Eigapment Trading LLC



Forecaste port side installation complete.




Silvagrip



Surface Finishing Eigispresent Trading LLC






Silvagrip



Surface Finishing Eigelpinisht Trading LLC





Silvagrip



Surface Finishing Eigelpinisht Trading LLC



End of Report:

Sohail Ghori General Manager





Surface Finishing Equipment Trading LLC

Abu Dhabi +971 505786978

sohail@sfeg.co.uk





Surface Finishing Eigelpment Trading LLC







Surface Finishing Eigelpinisht Trading LLC